



10/125 & 10/130 Precision Matched Passive LMA Double Clad Fibers

Nuferm's large mode area (LMA) and Polarization Maintaining LMA (PLMA) passive double clad fibers are ideally suited for applications spanning military, industrial and medical including linearly polarized fiber lasers and amplifiers. These fibers feature a 10 micron diameter core and 125 (PLMA) or 130 (LMA) micron diameter clad size with a low NA (0.075) core. They are precision matched to their active Yb-doped 10/130 LMA and PLMA matched counterparts to ensure excellent splice compatibility and low loss. As with all Nuferm standard Large Mode Area (LMA) fibers, these fibers are proof-tested to 100 kpsi, an industry requirement for long term reliability. They utilize the latest fiber design and NuCOAT™ coating technology to ensure excellent preservation of beam quality and extended operating life demanded by today's industrial fiber laser applications. These precision matched fibers are available in both non-PM and PANDA-style PM fibers.

Typical Applications

- Pulsed fiber lasers and amplifiers
- Material processing
- LIDAR
- Non-linear optics / frequency doubling

Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design — Useful for transmitting high CW powers
- "Few" moded core design — Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence — Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

Optical Specifications

Operating Wavelength	1060 – 1600 nm
Core NA	0.075 ± 0.005
First Cladding NA (5%)	≥ 0.460
Core Attenuation	≤ 40.00 dB/km @ 1300 nm ≤ 20.00 dB/km @ 1200 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm
Birefringence	nominal 3×10^{-4}

Geometrical & Mechanical Specifications

Cladding Diameter	125.0 ± 1.0 μm
Core Diameter	11.0 ± 1.0 μm
Coating Diameter	245.0 ± 10.0 μm
Coating Concentricity	< 5.0 μm
Core/Clad Offset	≤ 0.70 μm
Clad Non-Circularity	N/A
Proof-test Level	≥ 100 kpsi (0.7 GN/m ²)

PLMA-GDF-10/125-M

LMA-GDF-10/130-M

Operating Wavelength	1060 – 1600 nm
Core NA	0.075 ± 0.005
First Cladding NA (5%)	≥ 0.46
Core Attenuation	≤ 40.0 dB/km @ 1300 nm ≤ 20.0 dB/km @ 1200 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm
Birefringence	N/A

Cladding Diameter	130.0 ± 1.0 μm
Core Diameter	11.0 ± 1.0 μm
Coating Diameter	245.0 ± 10.0 μm
Coating Concentricity	< 5.0 μm
Core/Clad Offset	≤ 0.70 μm
Clad Non-Circularity	≤ 0.5 %
Proof-test Level	≥ 100 kpsi (0.7 GN/m ²)

M05-A-023-A



These precision matched fibers are included in our precision matched sets - see PLMA-YDF-10/125-M and LMA YDF-10/130-M



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nuferm.com • www.nuferm.com • Nuferm products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nuferm can assist with your requirements.

NU0153- 03/19/2018