



# 20/400 Precision Matched Passive LMA Double Clad Fibers

Nuferm's Large Mode Area (LMA) and Polarization Maintaining LMA (PLMA) passive double clad fiber are ideal for high power fiber lasers and amplifiers used in military, industrial, and medical applications. These fibers feature a 20 micron diameter core and 400 micron diameter clad size with a low NA (0.065) core. They are precision matched to their active Yb-doped 20/400 LMA and PLMA matched counterparts to ensure excellent splice compatability and low loss. As with all Nuferm standard Large Mode Area (LMA) fibers, these fibers are proof-tested to 100 kpsi, an industry requirement for long term reliability. They utilize the latest fiber design and NuCOAT™ coating technology to ensure excellent preservation of beam quality and extended operating life at the high power levels demanded by today's industrial fiber laser applications. These precision matched fibers are available in both non-PM and PANDA-style PM fibers.

### Typical Applications

- High power fiber lasers
- CW and pulsed amplifiers
- Military, industrial and medical

### Features & Benefits

- NuCOAT™ fluoroacrylate coating — Greater fiber durability in extreme environmental operating & storage conditions
- LMA core design — Useful for transmitting high CW powers
- "Few" moded core design — Easy to maintain single mode LP01 beam through fiber & components
- PANDA-style stress structure for increased birefringence — Superior optical performance and uniformity
- All fiber proof tested to > 100 kpsi — Critical for ensuring long term reliability when coiling

### Optical Specifications

Operating Wavelength  
Core NA  
First Cladding NA (5%)  
Core Attenuation  
Cladding Attenuation  
Birefringence

### PLMA-GDF-20/400-M

1060 – 1600 nm  
0.065 ± 0.005  
≥ 0.46  
≤ 50.0 dB/km @ 1300 nm  
≤ 25.0 dB/km @ 1200 nm  
≤ 15.0 dB/km @ 1095 nm  
nominal  $4 \times 10^{-4}$

### LMA-GDF-20/400-M

1060 – 1600 nm  
0.065 ± 0.005  
≥ 0.46  
≤ 12.0 dB/km @ 1300 nm  
≤ 8.0 dB/km @ 1200 nm  
≤ 15.0 dB/km @ 1095 nm  
N/A

### Geometrical & Mechanical Specifications

Cladding Diameter  
Core Diameter  
Coating Diameter  
Core/Clad Offset  
Clad Non-Circularity  
Proof-test Level

395.0 ± 10.0 μm  
20.0 ± 1.5 μm  
550.0 ± 15.0 μm  
≤ 2.00 μm  
N/A  
≥ 100 kpsi (0.7 GN/m<sup>2</sup>)

395.0 ± 5.0 μm  
20.0 ± 1.5 μm  
550.0 ± 15.0 μm  
≤ 2.00 μm  
≤ 0.50 %  
≥ 100 kpsi (0.7 GN/m<sup>2</sup>)



M05-A-035-A

These precision matched fibers are included in our precision matched sets - see PLMA-YDF-20/400-M and LMA-YDF-20/400-M



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nuferm.com • www.nuferm.com • Nuferm products are manufactured under an ISO 9001:2008 certified quality management system.



Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nuferm can assist with your requirements.

NU0154- 06/17/2016