

1550-nm Single-Mode Double Clad Fibers

High power 1550 nm amplifiers based on double clad Er/Yb fibers are widely used in CATV and Telecom applications. The 1550 nm passive double clad fiber is ideal for use both as a pump and signal output fiber in combiners and as a laser delivery fiber. The high cut-off, bend insensitive design of this fiber ensures excellent signal confinement, while allowing for low splice loss to Er/Yb doped double clad fibers and industry standard SMF-28™ fiber. They are available in both non-PM design for traditional high power amplifiers and in PANDA-style PM design for high power coherent communications and frequency conversion applications.

Typical Applications

- · CATV and Telecom amplifiers
- · Laser delivery/fluorescence

Features & Benefits

- NuCOATIM fluorocrylate coating Greater fiber durability in extreme environmental operating & storage conditions
- Exceptional uniformity and core/clad concentricity Low connectorization losses
- · Bend insensitive Survives application in tight confines
- All fiber proof tested to > 100 kpsi Critical for ensuring long term reliability

Optical Specifications	PM-GDF-1550	SM-GDF-1550
Operating Wavelength	1450 – 1600 nm	1450 – 1600 nm
Core NA	0.120	0.120
First Cladding NA (5%)	≥ 0.46	≥ 0.460
Mode Field Diameter	10.5 ± 0.7 μm @ 1550 nm	10.5 ± 0.7 μm @ 1550 nm
Cutoff	1440 ± 80 nm	1440 ± 80 nm
Core Attenuation	≤ 2.0 dB/km @ 1550 nm	≤ 1.00 dB/km @ 1550 nm
Cladding Attenuation	≤ 15.0 dB/km @ 1095 nm	≤ 15.0 dB/km @ 1095 nm
Birefringence	2.5 × 10 ⁻⁴	N/A

Geometrical & Mechanical Specifications

Cladding Diameter
Core Diameter
Coating Diameter
Coating Concentricity
Core/Clad Offset
Prooftest Level

 $\begin{array}{lll} 130.0 \pm 1.0 \ \mu m & 125.0 \pm 1.0 \ \mu m \\ 9 \ \mu m & 9 \ \mu m \\ 245.0 \pm 10.0 \ \mu m & 245.0 \pm 10.0 \ \mu m \\ < 5.0 \ \mu m & < 5.0 \ \mu m \\ \geq 0.50 \ \mu m & \geq 100 \ kpsi \ (0.7 \ GN/m^2) & \geq 100 \ kpsi \ (0.7 \ GN/m^2) \end{array}$

Mos-A-051-A





